

AMENDMENTS TO THE CLAIMS:

Claims 1-3 (not entered).

Claim 4 (currently amended and reformatted): A pressure-sensitive adhesion sheet ~~{for a silicone oxide containing material}~~, which comprises a plastic film formed on at least one surface thereof a layer composed of an acrylic pressure-sensitive adhesive comprising a copolymer comprising:

(a) 60 to 95% by weight of an acrylic monomer represented by formula (1b):

$\text{CH}_2=\text{C}(\text{R}^1)\text{-COOR}^2$, ~~$\text{CH}_2=\text{C}(\text{R}^1)\text{COOR}^2$~~ wherein R^1 is a hydrogen atom or a methyl group; and R^2 is an alkyl group having 4 to 12 carbon atoms;

(b) 5 to 40% by weight of a N,N-disubstituted noncyclic (meth) acrylamide represented by formula (2b): $\text{CH}_2=\text{C}(\text{R}^3)\text{-CONR}^4\text{R}^5$, ~~$\text{CH}_2=\text{C}(\text{R}^3)\text{CONR}^4\text{R}^5$~~ wherein R^3 is a hydrogen atom or a methyl group, and; R^4 and R^5 are alkyl groups ~~or organic groups which are bonded to each other to form a hetero ring together with a N atom~~; and

(c) 0 to 10% by weight of a monomer having an acidic group, each based on the total content of components (a), (b) and (c) ~~a), b) and c)~~,

wherein the plastic film has a water vapor permeability of no greater than 500g/m²/24 hours ~~500g or less/m²/24 hours~~.

Claim 5 (currently amended): The pressure-sensitive adhesion sheet ~~{for a silicone oxide containing material}~~ of claim 4, wherein a gel percentage of the copolymer is 50 to 95% by weight.

Claim 6 (currently amended): The pressure-sensitive adhesion sheet ~~{for a silicone oxide containing material}~~ of claim 4, wherein the (meth) acrylate ~~acrylamide~~ represented by formula (1b) is selected from the group consisting of butyl (meth) acrylate, isobutyl (meth) acrylate, isoamyl (meth) acrylate, hexyl (meth) acrylate, heptyl (meth) acrylate, 2-ethylhexyl (meth) acrylate, isooctyl (meth) acrylate, isononyl (meth) acrylate, and isodecyl ~~isodecyl~~ (meth) acrylate.

Claim 7 (currently amended): The pressure-sensitive adhesion sheet ~~{for a silicone oxide containing material}~~ of claim 4, wherein the (meth) acrylamide represented by formula (2b) is selected from the group consisting of N,N-dimethyl (meth) acrylamide, N,N-diethyl (meth) acrylamide, and N,N-dibutyl (meth) acrylamide, ~~N-(meth) acryloylmorpholine, N-(meth) acryloylpyrrolidone, N-(meth) acryloylpiperidine, N-(meth) acryloylpyrrolidine and N-(meth) acryloyl-4-peperidone.~~

Claim 8 (currently amended): The pressure-sensitive adhesion sheet ~~{for a silicone oxide containing material}~~ of claim 4, wherein the monomer having an acidic group is a carboxyl-containing monomer or a phosphoric group-containing monomer.

Claims 9-15 (canceled).

Claim 16 (not entered).

Claim 17 (currently amended): The pressure-sensitive adhesion sheet of claim ~~Claim~~ 8 wherein the monomer having an acidic group is selected from the group consisting of acrylic acid, methacrylic acid, itaconic acid, maleic acid, crotonic acid, 2-hydroxyethylacryloyl phosphate and 2-hydroxypropylacryloyl phosphate.

Claims 18-19 (canceled).